

R2

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 06-093412

(43)Date of publication of application : 05.04.1994

(51)Int.Cl.

C23C 10/28
// C22C 14/00

(21)Application number : 03-270165

(71)Applicant : NIPPON KARORAIKU KOGYO KK
TOYOTA MOTOR CORP

(22)Date of filing : 21.09.1991

(72)Inventor : SHAMOTO HIROYUKI
MORIKAWA TAKASHI
YOSHIKAWA RIHEI
SUEYASU MASANOBU

(54) HEAT RESISTANT TI-BASED ALLOY

(57)Abstract:

PURPOSE: To improve the oxidation resistance of an Al-Cr diffusion coating layer by forming the Al-Cr diffusion coating layer having a specified compsn. on the surface of a Ti-Al alloy.

CONSTITUTION: An Al-Cr diffusion coating layer constituted of, by weight, 50 to 65% and 0.5 to 7% Cr, and the balance Ti is formed on the surface of a Ti-based alloy contg. about 14 to 36% Al. As for the formation for this Al diffusion coating layer, diffusion coating by a powdery method, a thermal spraying method, a build up welding, a PVD method, a CVD method, etc., can be adopted. The thickness of the coating layer is suitably regulated to about 15 to 300 μ m. Furthermore, in the case the Al-Cr alloy layer is formed on the surface layer of the Ti-based alloy base metal, the alloy layer is brought into a diffusion reaction in the using process in a high temp. oxidizing atmosphere to form the Al-Cr diffusion coating layer, by which oxidation resistance is manifested.

LEGAL STATUS

[Date of request for examination]

25.03.1997

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

2922346

[Date of registration]

30.04.1999

[Number of appeal against examiner's decision of rejection]

BEST AVAILABLE COPY